



# DAIKOFCW 904L



SUPERAUSTENITIC STEELS  
904L

## DESCRIPTION

### Rutile flux cored wire for flat and horizontal position

Rutile flux-cored wire for welding and cladding in flat and horizontal position austenitic stainless alloys of the 20% Cr, 25% Ni, 5% Mo, 1.5% Cu, low C types. Its weld metal has good resistance to stress corrosion and intergranular corrosion and shows very good resistance to attack in non-oxidising acids. The resistance to crevice corrosion is better than that of ordinary 18% Cr, 8% Ni, Mo steels. The alloy is widely used in many applications related to the process industry.

## SPECIFICATIONS

ISO 17633-A	T Z 20 25 5 Cu L R M 3	AWS A5.22	(E385T0-4)
DIN	-	Werkstoff Number	-
Certifications	-	Shielding	M21
Positions	PA, PB, PC	Current	DC+

ASME QUALIFICATIONS	FERRITE	PREN	HARDNESS
F-No (QW432)	6	-	37.17
A-No (QW442)	-		


CHEM. COMP. %	DEFAULT	MECHANICAL PROPERTIES	MIN	VARIANT
C	0.03	Tensile strength R <sub>m</sub> MPa	510	660
Mn	3	Yield strength R <sub>p0.2</sub> MPa	320	410
Ni	25.5	Elongation A (L <sub>0</sub> =5d <sub>0</sub> ) %	25	35
Cr	21	Impact Charpy ISO-V	-	50J @ -196°C
P	0.02	Impact Charpy ISO-V	-	-
S	0.008			
		WELDING PARAMETERS	1.2 mm	1.6 mm
Mo	4.9	Ampere	130A - 280A	200A - 350A
Si	0.5	Voltage	22V - 30V	28V - 32V
Cu	1.6	Packaging	Ø 1,2÷1,6mm	Ø 1,2÷1,6mm
		Packaging Type	BS300 spool	BS300 spool

V 01/2024



The information in this datasheet is the result of detailed research and is considered accurate as of the publication date. However, we cannot guarantee its complete accuracy, and it is subject to change without notice. Actual results may vary due to many factors like welding procedures, material composition, temperature conditions, bevel configuration, and specific manufacturing techniques. We accept no liability for any errors or omissions in this datasheet. For the most current information, please visit [www.daikowelding.com](http://www.daikowelding.com).





# 904L

DESCRIPTION

SUPERAUSTENITIC STEELS

904L

## APPLICATION

Known for delivering a fully austenitic, low-carbon weld metal enriched with Mo and Cu, these consumables exhibit exceptional resistance to corrosion in sulphuric, phosphoric, and various inorganic and organic acids. Not the typical choice for environments demanding resistance to concentrated nitric acid, they excel in scenarios involving severe chloride pitting media, where opting for overmatching nickel base weld metal, such as alloy 625, is recommended. Noteworthy as the preferred weld metal for certain lower alloy austenitics like Creusot UHB 34L and UHB 734L, especially in wet process phosphoric acid service, these consumables find versatile applications. Their usage spans tanks, process vessels, piping systems, agitators, rotors, and cast pumps and valves, catering to the needs of fertilizer, phosphoric, sulphuric, and acetic acid plants. Additionally, they prove invaluable in salt and seawater environments and are enlisted in select offshore applications, including overlays on mild and low alloy steels. The welding process mandates no preheat or post-weld heat treatment (PWHT), with interpass temperatures carefully regulated to a maximum of 150°C. It's crucial to exercise control over heat input, especially when utilizing larger diameter shielded metal arc welding (SMAW) electrodes.

## ALLOY TYPE

904L is a nominally 20%Cr-25%Ni-5%Mo-2%Cu alloy with good corrosion resistance.

## MICROSTRUCTURE

In the as-welded condition the weld metal microstructure is fully austenitic.

## MATERIALS

Suitable for copper-free variants of the listed alloys and also to overmatch leaner alloys such as 317L, 317LN, 317LM, 317LMN, 1.4439, 1.4440 and S31726.

**EN W.Nr.:** 1.4505 (X4NiCrMoCuNb20-18-2), 1.4506 (X5NiCrMoCuTi 20-18), 1.4536 (GX2NiCrMoCuN25-20), 1.4539 (X1CrNiMoCuN25-20-5), 1.4585 (G-X7CrNiMoCuNb1818), 1.4500 (G-X7NiCrMoCuNb2520).

**ASTM:** N08904.

**PROPRIETARY:** Uddelholm 904L (voestalpine), 2RK65 (Sandvik), Cronifer 1925LC (VDM), 2545LX (Outokumpu), Uranus® B6, B6M (Industeel).

V 01/2024



The information in this datasheet is the result of detailed research and is considered accurate as of the publication date. However, we cannot guarantee its complete accuracy, and it is subject to change without notice. Actual results may vary due to many factors like welding procedures, material composition, temperature conditions, bevel configuration, and specific manufacturing techniques. We accept no liability for any errors or omissions in this datasheet. For the most current information, please visit [www.daikowelding.com](http://www.daikowelding.com).

 **DAIKO**®