



DAIKOWM 9CrMo



CREEP RESISTING STEELS

9CrMo

DESCRIPTION

9%Cr-1%Mo solid wire for elevate temperature service

Especially formulated for 9% Cr 1% Mo alloyed steels and steels for pressurized hydrogen service, particularly in oil refineries prolonged elevated temperature service up to about 650°C, especially in oil refineries (piping, heat exchangers, pressure vessels, boiler superheater). The easy handling and the high deposition rate result in high productivity, excellent welding performance and very low spatter formation. The wire shows good wetting behaviour and a finely rippled surface pattern.

SPECIFICATIONS

ISO 21952-A	G CrMo 9 Si	AWS A5.28	ER80S-B8
DIN	-	Werkstoff Number	-
Certifications	-	Shielding	M20, M21
Positions	PA, PB, PC, PD, PE, PF	Current	DC+

ASME QUALIFICATIONS

F-No (QW432)	6
A-No (QW442)	5

FERRITE

-

PREN

-

HARDNESS

-

CHEM. COMP. %

DEFAULT

C	0.07
Mn	0.6
Ni	0.1
Cr	9
P	0.015
S	0.01
Mo	1
Si	0.5
Cu	0.1

MECHANICAL PROPERTIES

	MIN	VARIANT
Tensile strength R_m MPa	550	710
Yield strength $R_{p0.2}$ MPa	470	590
Elongation A ($L_0=5d_0$) %	17	23
Impact Charpy ISO-V	-	40J @ -20°C
Impact Charpy ISO-V	-	-

WELDING PARAMETERS

	1 mm	1.2 mm
Ampere	180A - 240A	190A - 250A
Voltage	22V - 29V	26V - 30V
Packaging	Ø 0,8÷1,6mm	Ø 0,8÷1,6mm
Packaging Type	Drums, B300, D200 and D100 spools.	Drums, B300, D200 and D100 spools.

V 01/2024



The information in this datasheet is the result of detailed research and is considered accurate as of the publication date. However, we cannot guarantee its complete accuracy, and it is subject to change without notice. Actual results may vary due to many factors like welding procedures, material composition, temperature conditions, bevel configuration, and specific manufacturing techniques. We accept no liability for any errors or omissions in this datasheet. For the most current information, please visit www.daikowelding.com.





9CrMo

DESCRIPTION

CREEP RESISTING STEELS

9CrMo

APPLICATION

Designed for elevated temperature applications, this alloy offers a commendable level of corrosion resistance in demanding environments like superheated steam, hot hydrogen gas, and high-Sulphur crude oils. It surpasses the performance of 5%Cr-0.5%Mo steels, making it the preferred choice when elevated performance is essential. Well-suited for welding heat-treatable, quenched, and subsequently tempered steels, as well as for tubes resistant to caustic embrittlement, this alloy proves its versatility in a range of applications. It confidently handles working temperatures up to 600°C. Primarily deployed in oil refineries and power plants, this alloy excels in critical components such as boiler superheater tubing, heat exchangers, piping, and pressure vessels. Its reliability and superior performance make it an optimal solution for high-temperature and corrosive environments in these industrial settings

ALLOY TYPE

9%Cr-1%Mo martensitic alloy for elevated temperature service.

MICROSTRUCTURE

In the PWHT condition the microstructure consists of tempered bainite.

MATERIALS

EN W.Nr.: X12CrMo 9 1 (1.7386), X7CrMo 9 1 (1.7388), G5-12CrMo 10 1 (1.7389).

ASTM: A387 gr. 9, A335 gr. 9, A234 gr. WP9 (fittings), A199 gr. T9, A213 gr. T9, A182 gr. F9, A336 gr. F9, A217 gr. C12.

WELDING & PWHT

Due to the inherent hardness observed in the as-deposited state, reaching values of up to 450HV, and the relatively diminished fracture resistance characteristic of the martensitic 9CrMo microstructure, it is imperative to implement a preheat and maintain a minimum interpass temperature of 200°C to prevent hydrogen-induced cracking. Ensuring electrodes are meticulously controlled and handled is crucial to achieve weld metal with hydrogen levels below 5ml/100g. In the context of TIG root runs or all-TIG welds, consideration may be given to a lower preheat of 150°C. During welding, complete transformation within the working range of 200-350°C may not be achieved. Therefore, partial cooling to around 150°C is recommended before direct transfer to Post-Weld Heat Treatment (PWHT), followed by Non-Destructive Examination (NDE). If PWHT is intended after complete cool-out and NDE, maintaining the preheat temperature for a specified duration, according to thickness, is advisable to promote effective hydrogen dispersal. Notably, this precaution holds less significance for TIG and solid wire MAG processes. PWHT to temper the weldment typically falls within the range of 705-780°C, as outlined in ASME B31.3 (e.g., 705-760°C). The minimum recommended holding time for this process is two hours. For castings, the suggested minimum PWHT temperature is lower, with specified temperatures as low as 670°C.

V 01/2024



The information in this datasheet is the result of detailed research and is considered accurate as of the publication date. However, we cannot guarantee its complete accuracy, and it is subject to change without notice. Actual results may vary due to many factors like welding procedures, material composition, temperature conditions, bevel configuration, and specific manufacturing techniques. We accept no liability for any errors or omissions in this datasheet. For the most current information, please visit www.daikowelding.com.

 **DAIKO**