



DAIKOWM Mo.B



CREEP RESISTING STEELS

0.5Mo

DESCRIPTION

Copper coated rod for creep resisting 1/2Mo steels

Rod wire designed for prolonged elevated temperature service up to about 450°C for welding of low alloy and creep resistant steels. Application area includes boiler, pressure vessel, tanks, pipeline, and crane constructions as well as in structural steel engineering.

SPECIFICATIONS

ISO 21952-A	G MoSi	AWS A5.28	ER70S-A1
DIN	-	Werkstoff Number	-
Certifications	-	Shielding	M20, M21
Positions	PA, PB, PC, PD, PE, PF	Current	DC+

ASME QUALIFICATIONS

F-No (QW432)	6
A-No (QW442)	2

FERRITE

-

PREN

-

HARDNESS

-

CHEM. COMP. %

DEFAULT

C	0.09
Mn	1.2
Ni	0.15
Cr	0.15
P	0.01
S	0.01
Mo	0.5
Si	0.6
Cu	0.25

MECHANICAL PROPERTIES

	MIN	VARIANT
Tensile strength R _m MPa	515	640
Yield strength R _{p0.2} MPa	400	530
Elongation A (L ₀ =5d ₀) %	19	26
Impact Charpy ISO-V	-	90J @ -20°C
Impact Charpy ISO-V	-	-

WELDING PARAMETERS


	1 mm	1.2 mm
Ampere	180A - 240A	190A - 250A
Voltage	22V - 29V	26V - 30V
Packaging	Ø 0,8÷1,6mm	Ø 0,8÷1,6mm
Packaging Type	Drums, B300, D200 and D100 spools.	Drums, B300, D200 and D100 spools.

V 01/2024



The information in this datasheet is the result of detailed research and is considered accurate as of the publication date. However, we cannot guarantee its complete accuracy, and it is subject to change without notice. Actual results may vary due to many factors like welding procedures, material composition, temperature conditions, bevel configuration, and specific manufacturing techniques. We accept no liability for any errors or omissions in this datasheet. For the most current information, please visit www.daikowelding.com.





0.5Mo

DESCRIPTION

CREEP RESISTING STEELS

0.5Mo

APPLICATION

Incorporating a nominal 0.5% Mo alloying element, this alloy delivers improved elevated temperature performance compared to C-Mn steels. It is utilized in crafting vessels and associated pipework, specifically designed for applications demanding exceptional creep rupture strength and ductility at temperatures up to approximately 450°C. The Mo content also enhances resistance to hydrogen attack during chemical process plant operations. These consumables exhibit favorable mechanical properties in both as-welded and stress-relieved weld metal, proving valuable in welding structural and general engineering steels for service in ambient or sub-zero temperatures. Notably related to higher-strength manganese-molybdenum alloyed steel consumables, the welding process involves preheat and interpass temperatures typically ranging from 100-250°C, depending on the thickness being welded and restraint. The post-weld tempering heat treatment (PWHT) temperature varies per code, ranging from 550°C to 720°C, with the most common range being 630-670°C. Some codes permit omitting PWHT for materials up to 20mm thick.

ALLOY TYPE

Ferritic creep resisting 0.5%Mo steels for elevated temperature service.

MICROSTRUCTURE

In the stress-relieved condition the microstructure consists of acicular ferrite with some tempered bainite.

MATERIALS

EN W.Nr.: 10028-2 gr. 16Mo3 (1.5415), 16Mo5 (1.5423), 10MnMo 4 5 (1.5424), 11MnMo 4 5 (1.5425), GS-22Mo 4 (1.5419).

ASTM: A335 gr. P1, A209 & A 250 gr. T1, A336 gr. F1, A204 gr. A, B, C, A217 gr. WC1, A352 gr. LC1.

V 01/2024



The information in this datasheet is the result of detailed research and is considered accurate as of the publication date. However, we cannot guarantee its complete accuracy, and it is subject to change without notice. Actual results may vary due to many factors like welding procedures, material composition, temperature conditions, bevel configuration, and specific manufacturing techniques. We accept no liability for any errors or omissions in this datasheet. For the most current information, please visit www.daikowelding.com.

DAIKO