



# DAIKOWT 120

GTAW

HIGH YIELD STRENGTH STEELS

120ksi

## DESCRIPTION

### Low alloy solid wire for high yield strength steels

High-strength, medium alloy solid wire electrode for shielded arc welding of quenched and tempered fine grained structural steels. It is designed for those applications requiring 120 Ksi minimum tensile strength and good charpy v-notch toughness, such as when welding HY-80, HY-100, Strenx® 900, S890QL, S960Q. These materials are used in lifting and handling machines, bridges, tanks, shipbuilding, railway sector, mines, frames, crane fabrication, trailer construction, and other structural applications involving higher strength materials.

## SPECIFICATIONS

ISO 16834-A	W 89 4 Mn4Ni2,5CrMo	AWS A5.28	ER120S-G
DIN	-	Werkstoff Number	-
Certifications	-	Shielding	11
Positions	PA, PB, PC, PD, PE, PF	Current	DC-

## ASME QUALIFICATIONS

F-No (QW432)	6
A-No (QW442)	-

## FERRITE

F-No (QW432)	-
A-No (QW442)	-

## PREN

F-No (QW432)	-
A-No (QW442)	-

## HARDNESS

F-No (QW432)	-
A-No (QW442)	-

## CHEM. COMP. %

	DEFAULT
C	0.11
Mn	1.9
Ni	2.4
Cr	0.6
P	0.01
S	0.01
Mo	0.6
Si	0.8
Cu	0.15

## MECHANICAL PROPERTIES

	MIN	VARIANT
Tensile strength R <sub>m</sub> MPa	940	980
Yield strength R <sub>p0.2</sub> MPa	890	890
Elongation A (L <sub>0</sub> =5d <sub>0</sub> ) %	15	16
Impact Charpy ISO-V	-	60J @ -40°C
Impact Charpy ISO-V	-	-

## WELDING PARAMETERS

	1.6 mm	2.4 mm
Ampere	95A - 135A	145A - 205A
Voltage	-	-
Packaging	Ø 1,2÷3,2mm	Ø 1,2÷3,2mm
Packaging Type	5kg carton tube	5kg carton tube

V 01/2024



The information in this datasheet is the result of detailed research and is considered accurate as of the publication date. However, we cannot guarantee its complete accuracy, and it is subject to change without notice. Actual results may vary due to many factors like welding procedures, material composition, temperature conditions, bevel configuration, and specific manufacturing techniques. We accept no liability for any errors or omissions in this datasheet. For the most current information, please visit [www.daikowelding.com](http://www.daikowelding.com).





# 120ksi

DESCRIPTION

HIGH YIELD STRENGTH STEELS

120ksi

## APPLICATION

Designed for applications demanding a minimum tensile strength of 120 Ksi and excellent Charpy V-notch toughness, these consumables are suitable for diverse structural uses. From lifting machines to shipbuilding, railway sectors to crane fabrication, they find application in various high-strength scenarios. Preheat as per base material and thickness; generally, a 100°C minimum preheat is needed for materials requiring these high-strength consumables. Exercise caution with some HSLA steels, as interpass temperatures above 200°C may compromise strength and toughness. Post-weld heat treatment (PWHT) depends on the base material and application.

## ALLOY TYPE

Mn-Ni-Mo low alloy consumables for welding high strength steels with ultimate tensile strength up to 825 MPa (120 ksi).

## MICROSTRUCTURE

The microstructure of all the consumables is predominantly ferrite; some will contain high proportions of acicular ferrite for optimum aswelded toughness

## MATERIALS

This material is used for a variety of high strength steels. HY-80, HY-90, HY- 100. S890 and higher strength grades, thermo mechanically treated fine grain steels.

**EN W.Nr.:** S890QL, S960Q.

**ASTM:** A 709 Gr. 100 Type B, E, F, H, Q, HPS 100W.

**PROPRIETARY:** Strenx® 900 (SSAB), Alform® 900 X-treme (voestalpine).

V 01/2024



The information in this datasheet is the result of detailed research and is considered accurate as of the publication date. However, we cannot guarantee its complete accuracy, and it is subject to change without notice. Actual results may vary due to many factors like welding procedures, material composition, temperature conditions, bevel configuration, and specific manufacturing techniques. We accept no liability for any errors or omissions in this datasheet. For the most current information, please visit [www.daikowelding.com](http://www.daikowelding.com).

 **DAIKO**