



DESCRIPTION

Solid rod for welding 2%Ni steel

Rod wire designed for welding low-alloyed steels for low temperature applications. Typically, they are used for welding 2.5% Nickel steels and other materials requiring good toughness at temperatures as low as -60°C.

SPECIFICATIONS

ISO 14341-A	W 50 6 M21 2Ni2	AWS A5.28	ER80S-Ni2
DIN	-	Werkstoff Number	-
Certifications	-	Shielding	I1
Positions	PA, PB, PC, PD, PE, PF	Current	DC-

ASME QUALIFICATIONS

F-No (QW432)	6
A-No (QW442)	10

FERRITE

-

PREN

-

HARDNESS

-

CHEM. COMP. %

DEFAULT

C	0.09
Mn	1.1
Ni	3.5
P	0.01
S	0.01
Mo	0.03
Si	0.55
Cu	0.12


MECHANICAL PROPERTIES

	MIN	VARIANT
Tensile strength R _m MPa	550	590
Yield strength R _{p0.2} MPa	500	520
Elongation A (L ₀ =5d ₀) %	24	25
Impact Charpy ISO-V	47J @ -60°C	50J @ -60°C
Impact Charpy ISO-V	-	-

WELDING PARAMETERS

	1.6 mm	2.4 mm
Ampere	95A - 135A	145A - 205A
Voltage	-	-
Packaging	Ø 1,2÷3,2mm	Ø 1,2÷3,2mm
Packaging Type	5kg carton tube	5kg carton tube





2Ni

DESCRIPTION

CRYOGENIC STEELS

2Ni

APPLICATION

Ideal for fabricating storage tanks, process plants, and associated pipework, especially in scenarios demanding good fracture toughness from as-welded joints, even in temperatures as low as -60°C . The addition of approximately 2.5% Ni enhances microstructural refinement and procedural tolerance compared to plain CMn weld metal. It also supports the formation of a stable patina, meeting the characteristics of weathering steels, offering an alternative to using matching consumables. Preheating should align with the base material and its thickness. While AWS consumable specifications may recommend PWHT, many fabrications may be left as-welded, with the necessity for PWHT generally determined by applicable design codes.

ALLOY TYPE

Nominally 2,5%Ni low alloy steels.

MICROSTRUCTURE

In the as-welded condition the microstructure is ferritic with a component of acicular ferrite for optimum toughness.

MATERIALS

Low temperature applications, fine-grained steels that contain up to 2.5% Nickel.

ASTM: A203 gr. A & B plate, A333 gr. 6 pipe, A350 gr. LF1 & LF2 forgings, A352 gr. LC2 casting.

API: 5L X52, 5L X56, 5L X60, 5L X65.

V 01/2024



The information in this datasheet is the result of detailed research and is considered accurate as of the publication date. However, we cannot guarantee its complete accuracy, and it is subject to change without notice. Actual results may vary due to many factors like welding procedures, material composition, temperature conditions, bevel configuration, and specific manufacturing techniques. We accept no liability for any errors or omissions in this datasheet. For the most current information, please visit www.daikowelding.com.

DAIKO