



DAIKOWT 347Si

GTAW

AUSTENITIC STAINLESS STEELS

347

DESCRIPTION

Solid rod for stabilised austenitic stainless steels

These Cr-Ni consumables are Nb-stabilized for welding steels that are stabilized with Ti or Nb. Nb it reduces intergranular corrosion under severe operation conditions. Also suitable for cladding as on mild steel after a 309 buffer layer. Service temperatures are typically -100°C to about 400°C. The higher silicon content (if compared with standard 347) increases the welding fluidity and improve the bead appearance.

SPECIFICATIONS

ISO 14343-A	W 19 9 Nb S	AWS A5.9	ER347Si
DIN	-	Werkstoff Number	-
Certifications	CE	Shielding	11
Positions	PA, PB, PC, PD, PE, PF	Current	DC-

ASME QUALIFICATIONS

F-No (QW432)	6
A-No (QW442)	8

FERRITE

3-12 FN

PREN

19.165

HARDNESS

84HRB

CHEM. COMP. %

DEFAULT

C	0.05
Mn	0.7
Ni	10
Cr	19
Nb	0.4
P	0.02
S	0.01
Mo	0.05
Si	0.9
Cu	0.07

MECHANICAL PROPERTIES

	MIN	VARIANT
Tensile strength R_m MPa	550	660
Yield strength $R_{p0.2}$ MPa	350	450
Elongation A ($L_0=5d_0$) %	25	42
Impact Charpy ISO-V	-	150J @ -50°C
Impact Charpy ISO-V	-	-

WELDING PARAMETERS

	1.6 mm	2.4 mm
Ampere	80A - 100A	110A - 160A
Voltage	-	-
Packaging	Ø 1,0÷4,0 mm	Ø 1,0÷4,0 mm
Packaging Type	5kg carton tube	5kg carton tube

V 01/2024



The information in this datasheet is the result of detailed research and is considered accurate as of the publication date. However, we cannot guarantee its complete accuracy, and it is subject to change without notice. Actual results may vary due to many factors like welding procedures, material composition, temperature conditions, bevel configuration, and specific manufacturing techniques. We accept no liability for any errors or omissions in this datasheet. For the most current information, please visit www.daikowelding.com.

DAIKO



347

DESCRIPTION

AUSTENITIC STAINLESS STEELS

347

APPLICATION

Developed for welding Ti and Nb-stabilized 18Cr/8Ni stainless steel types 321 and 347, they are also suitable for unstabilized grades like 304/304L. Service temperatures typically range from -100°C to about 400°C. The applications parallel those of 308L, covering diverse sectors such as food, brewery, pharmaceutical equipment, architectural and general fabrication, and nuclear engineering. However, the 347 consumables mentioned here are generally unfit for elevated temperature structural applications where 0.04-0.08% carbon is specified for creep resistance; for such cases, consult data sheets 347H. For cryogenic uses requiring >0.38mm (15mils) Charpy lateral expansion at -196°C, select unstabilized weld metal with low carbon and controlled ferrite. No preheating requirement, a recommended maximum interpass temperature of 250°C, and no post-weld heat treatment (PWHT) necessity.

ALLOY TYPE

347 austenitic stainless steel for joining 321 and 347 base materials.

MICROSTRUCTURE

Austenite with a controlled level of ferrite, normally in the range 3-12FN.

MATERIALS

EN W.Nr.: 1.4541, 1.4543, 1.4561, 1.4550, 1.4552 (cast).

ASTM: 321, 347, CF8C (cast).

UNS: S32100, S34700.

