



G-TECH 90G

SMAW

HIGH YIELD STRENGTH STEELS
80-90ksi

DESCRIPTION

Basic coated electrode for high strength low alloy steels

This basic coated welding electrode deposits a low alloyed very tough weld metal with high tensile strength and yield point with a stable arc, regular deposit and easy deslagging. Used to weld steel with tensile strength between 620 and 760 N/mm². During the use adopt preheat, interpass temperature and post weld treatment as required by the base material. Used to join cast steels, pipes, boilers, pressure vessel, bearing frameworks. It can also be used to join fine grain high strength low alloy steels for construction, pressure vessels and pipes.

SPECIFICATIONS

ISO 18275-A	E 62 4 1NiMo B 42	AWS A5.5	E9018-G
DIN	-	Werkstoff Number	-
Certifications	-	Shielding	-
Positions	PA, PB, PC, PD, PE, PF	Current	DC+, AC

ASME QUALIFICATIONS

F-No (QW432)	4
A-No (QW442)	3

FERRITE

FERRITE	-
---------	---

PREN

PREN	-
------	---

HARDNESS

HARDNESS	-
----------	---

CHEM. COMP. %

CHEM. COMP. %	DEFAULT
C	0.07
Mn	1.15
Ni	0.8
Cr	0.05
P	0.01
S	0.01
Mo	0.4
Si	0.6
Cu	0.1

MECHANICAL PROPERTIES

MECHANICAL PROPERTIES	MIN	VARIANT
Tensile strength R _m MPa	620	730
Yield strength R _{p0.2} MPa	620	670
Elongation A (L ₀ =5d ₀) %	17	22
Impact Charpy ISO-V	47J @ -40°C	70J @ -20°C
Impact Charpy ISO-V	-	50J @ -40°C

WELDING PARAMETERS

WELDING PARAMETERS	2.5 mm	3.2 mm	4 mm	
Ampere	70A - 90A	100A - 140A	140A - 180A	180A -
Voltage	-	-	-	-
Packaging	52 pcs/kg	21 pcs/kg	14 pcs/kg	9 pcs/kg
Packaging Type	Carton box	Carton box	Carton box	Carton box

V 01/2024



The information in this datasheet is the result of detailed research and is considered accurate as of the publication date. However, we cannot guarantee its complete accuracy, and it is subject to change without notice. Actual results may vary due to many factors like welding procedures, material composition, temperature conditions, bevel configuration, and specific manufacturing techniques. We accept no liability for any errors or omissions in this datasheet. For the most current information, please visit www.daikowelding.com.

DAIKO



80-90ksi

DESCRIPTION

HIGH YIELD STRENGTH STEELS

80-90ksi

APPLICATION

Recommended for high-strength low-alloy steels with a minimum yield strength of up to 540MPa, these consumables offer enhanced elevated temperature performance compared to CMn steels. They are employed in fabricating vessels and associated pipework, catering to the demand for exceptional creep rupture strength and ductility, as high as 450°C. Demonstrating good toughness at low temperatures, they are ideal for crafting higher-strength steels intended for stress-relieved conditions. Specifically designed for offshore oil well-head process pipework and fittings, these low-nickel consumables meet NACE MRO175 requirements (<1% Ni & <22 HRC), ensuring resistance to sulphide-induced stress corrosion cracking in sour service, coupled with impressive sub-zero toughness. Additionally, they find utility in repairing medium-strength, low-alloy steel castings, especially in cases where stress relief alone (rather than normalizing and tempering) is applied. The actual preheat and post-weld heat treatment (PWHT) specifications hinge on the base material being welded, typically falling within the range of 100-250°C for preheat/interpass temperatures, with PWHT being a mandatory step in these applications.

ALLOY TYPE

Low alloy steel consumables with MnMo additions for welding high strength steels with ultimate tensile strength to 620 MPa (90ksi).

MICROSTRUCTURE

In the stress relieved condition the microstructure consists of tempered bainite.

MATERIALS

EN W.Nr.: P295 G H, P355 G H, 16Mo2, 17Mo3, 14Mo6, S275, S355, S420, S275, S355, S420.

ASTM: A 487 Gr 2A, 2B & 2C.

