



G-TECH 99

SMAW

CAST IRON
Ni CI

DESCRIPTION

Pure nickel basic-graphite coated electrode for cast iron

Basic-graphite special coated electrode with a pure nickel core wire. Suitable for cold welding on grey cast iron, malleable cast iron, and cast steel as well as repair welding on castings showing symptoms of fatigue. Excellent welding properties also for welding with low amperage. Quietly and intensely flowing weld metal, only few spattering, easily removable slag. The weld seam is soft and machinable even in the transitional zone between the seam and the base material.

SPECIFICATIONS

ISO 1071	E C Ni-CI 1	AWS A5.15	ENi-CI
DIN	-	Werkstoff Number	-
Certifications	-	Shielding	-
Positions	PA, PB, PC, PD, PE, PF	Current	DC+

ASME QUALIFICATIONS	FERRITE	PREN	HARDNESS
F-No (QW432)	-	-	170HB
A-No (QW442)	-	-	

CHEM. COMP. %	DEFAULT	MECHANICAL PROPERTIES	MIN	VARIANT
C	1	Tensile strength R_m MPa	270	300
Mn	0.2	Yield strength $R_{p0.2}$ MPa	250	270
S	0.02	Elongation A ($L_0=5d_0$) %	6	8
Si	0.7	Impact Charpy ISO-V	-	-
Fe	3	Impact Charpy ISO-V	-	-

WELDING PARAMETERS	2.5 mm	3.2 mm	4 mm
Ampere	70A - 90A	90A - 120A	120A - 140A
Voltage	-	-	-
Packaging	pcs/kg	pcs/kg	pcs/kg
Packaging Type	Carton box	Carton box	Carton box



The information in this datasheet is the result of detailed research and is considered accurate as of the publication date. However, we cannot guarantee its complete accuracy, and it is subject to change without notice. Actual results may vary due to many factors like welding procedures, material composition, temperature conditions, bevel configuration, and specific manufacturing techniques. We accept no liability for any errors or omissions in this datasheet. For the most current information, please visit www.daikowelding.com.



V 01/2024



Ni CI

DESCRIPTION

CAST IRON
Ni CI

APPLICATION

Pure nickel consumables serve a vital role in the welding and repair processes involving standard grades of grey cast irons and malleable cast irons. These consumables yield low-strength deposits, providing a distinct advantage as they can be easily machined, even when applied in thin layers. The inherent resistance to hardening in diluted weld metal enhances their utility, particularly for buttering applications prior to the use of more economically efficient NiFe consumables. Beyond their primary applications, pure nickel consumables demonstrate versatility by facilitating the joining of these cast irons with other materials, including steels, monels, copper, etc. This proves especially beneficial in scenarios where high strength is not the foremost requirement. Typical components that benefit from the application of pure nickel consumables include a wide array of general engineering castings. These encompass crucial elements such as machine bases, engine blocks, gear housings, and similar structures that operate under relatively low stresses. The adaptability and effectiveness of pure nickel consumables make them integral to the fabrication and maintenance of components in various engineering applications.

ALLOY TYPE

Pure nickel type for welding cast iron.

MICROSTRUCTURE

Austenitic nickel with finely distributed graphite.

MATERIALS

Grey iron.

EN W.Nr.: 1561:2011 Grey cast irons+

ASTM: A159, A319, A126, A48.

WELDING & PWHT

Welding is commonly performed without preheat, although scenarios involving heavy multipass deposits or highly restrained joints may necessitate preheat, potentially reaching up to 150°C. Before initiating the welding process, it is crucial to prepare surfaces meticulously, employing careful gouging and/or grinding with limited heat application to prevent the propagation of cracks. The designated welding area should be cleaned diligently, removing contaminants such as sand, oil, grease, paint, or rust to the greatest extent possible. Preheating proves advantageous for eliminating impregnated oil on used castings undergoing repairs. In instances where welding is conducted without preheat, it is advisable to minimize the width of the Heat-Affected Zone (HAZ) by utilizing a low heat input and maintaining a low interpass temperature. The application of a skip welding technique can be beneficial in achieving this objective. For welds involving thicker sections or highly restrained conditions, preheat up to 150°C may become imperative. Light peening, aimed at reducing contraction stresses, can offer additional benefits, though caution is warranted to prevent the depletion of weld metal ductility. Buttering the joint faces or the sides of the repair cavity before the filling process can be a desirable practice, whether or not preheat is applied. Upon completion of the welding process, it is recommended to allow the workpiece to cool gradually, with the option of using insulation if deemed necessary for optimal results.

